



- 100% Solids, High Build, Apply on steel or concrete
- Extraordinary color fastness for long term aesthetics (UVR Hardener)
- Chemically Fused Liquid Ceramic (CFLC) for extraordinary durability
- Meets LEED EQ 4.2 (Independent Laboratory Validation)
- Meets requirements for FDA & USDA inspected facilities

CFLC technology offers incredible abrasion resistance with excellent impact resistance. Standard technologies increase the hardness of a coating to achieve abrasion resistance which leads to brittleness. Advanced Hybrid Cycloaliphatic (AHC): AHC technology offers increased physical characteristics (strength, chemical resistance, durability), with those properties remaining stable over time. Standard technologies diminish rapidly over time. Choose UVR technology for 'Best in Class' resistance to yellowing over time.

## PRODUCT DESCRIPTION

LiquaTile 1143 is a 100% solids, AHC (Advanced Hybrid Cycloaliphatic) & CFLC (Chemically Fused Liquid Ceramic) self leveling floor coating which exhibits excellent resistance to chemicals while also displaying outstanding mechanical properties, such as adhesion, abrasion, and impact resistance. It is a full ceramic version of LiquaTile 1184. LiquaTile Epoxy Floor Coatings are designed for concrete service such as warehouse flooring, machine pads, pharmaceutical processing areas, USDA inspected facilities, and chemical processing areas.

## STORAGE

Keep well sealed containers in a cool, dry place. Avoid contact with sources of extreme hot or cold temperatures as well as direct sunlight. Containers should be stored at 40°F to 95°F. Shelf life is one (1) year if exposed to the above conditions.

## SAFETY

Prior to commencing work, carefully read and follow all SDS (formerly MSDS), Technical Data Sheets, and any instruction manuals for products and equipment used during installation. Following the safety regulations of job-site, local, state, and federal authorities is the responsibility of the installation company, general contractor, and/or facility owner.

## DISCLAIMER

This document does not purport to address all applicability and safety concerns, if any, associated with its use. It is the responsibility of the user to determine applicability of the information and products, and to establish appropriate safety practices.

## SPECIFYING CONSIDERATIONS

**Specifying LiquaTile 1143 is recommended when...**

- greater performance than industry standard products is required. LiquaTile 1143's AHC and CFLC technology gives it better wear, impact resistance, and chemical resistance than standard epoxies.
- longer life is desired. CFLC technology means the coating begins life with a much more robust structure than industry standard epoxies while AHC technology means the coating's properties will be long lasting, not rapidly degrading over time.
- longer retention of appearance is required. LiquaTile 1143 with UVR hardener will retain its appearance substantially longer than other general purpose coatings because of its AHC and CFLC ceramic technology.
- better color retention is required. While no epoxy is non-yellowing, LiquaTile 1143 with UVR Hardener has best in class color stability as compared to other epoxy coatings. If aesthetics is an issue, we recommend the use of a topcoat in direct sunlight.
- better chemical resistance is required. LiquaTile 1143's AHC technology gives it greater chemical resistance than normal epoxy coatings. Contact Wolverine Coatings Corporation (WCC) for recommendations for areas subject to aggressive chemical exposure.
- When good slip-resistance is required. Although LiquaTile 1143's surface is smooth, it has 50% better slip-resistance than typical coatings in its class.

**Specifying LiquaTile 1184 is NOT recommended when...**

- substrate is subject to high moisture vapor transmission. Contact WCC in this situation.
- LiquaTile 1143 will come into contact with harsh chemicals. LiquaTile 1143 has very good chemical resistance, but is not designed for extreme resistance. Contact WCC for a recommendation from our ChemShield line of coatings.
- LiquaTile 1143 will receive direct sunlight when color retention is required. LiquaTile 1143 has best in class color retention compared to normal epoxy coatings, but as with all epoxies, it is not non-yellowing. Consider specifying one of our non-yellowing coatings such as EnduraShield 2254.

## SPECIFYING CONSIDERATIONS (CONT.)

<b>Product Advantages</b>	<ul style="list-style-type: none"> <li>LiquaTile 1143 has much better physical properties than typical epoxy coatings on the market. Significant properties include better wear, abrasion, impact, and chemical resistance. Its color retention is also much better than other epoxy coatings.</li> <li>LiquaTile 1143 will retain its physical properties longer, rather than degrade rapidly like other epoxy coatings on the market.</li> </ul>
---------------------------	--

## OTHER PRODUCTS FOR SIMILAR USE

<b>Moisture Vapor Transmission Concerns</b>	Consider specifying BondTite 1503. Contact Wolverine Coatings Corporation in this situation.
<b>Crystal Clear Sealer</b>	LiquaTile 1143 is only available pigmented. Consider specifying BondTite 1115 100% solids epoxy coating. For areas exposed to sunlight and/or chemicals, consider specifying EnduraShield 2254 Urethane or HybriShield 2401 Polycarbonate coating.
<b>High Chemical Exposure</b>	Contact Wolverine Coatings Corporation for assistance.
<b>Light Wear Exposure</b>	Consider specifying LiquaTile 1184 or LiquaTex 1151

## SOLID (CURED) PHASE PHYSICAL DATA

PROPERTY	VALUE	TEST METHOD (If applicable)
<b>Finish</b>	Gloss / High Gloss (72±5)	ASTM D523
<b>Color</b>	Pigmented	ASTM D2244
<b>Flexural Modulus (Stiffness)</b>	N/T	ASTM D790
<b>Flexural Strength</b>	N/T	ASTM D790 - 10
<b>Compressive Strength</b>	N/T	ASTM D695 - 10
<b>Elongation</b>	2%	ASTM D638 - 10
<b>Coefficient of Friction</b>	1.53 dry / 1.20 wet	ASTM D2047
<b>Hardness (7 Days)</b>	> 75	ASTM D2240
<b>Abrasion Resistance (Taber)</b>	55 - 65 mg	ASTM D4060
<b>Bond Strength (Concrete)</b>	>1000 psi (Concrete fails)	ASTM D4541
<b>Impact Resistance (in./lbs/20 mils)</b>	44 - Direct, Zero Failure	ASTM D5420

<b>Chemical Resistance</b>	Xylene	S	Sodium hydroxide, 10%	S
I - Immersion/Continuous Service	1,1,1 Trichloroethane	S	Sodium hydroxide, 50%	S
C - Secondary Containment (72 Hr)	MEK	S	Battery acid	S
S - Splash/Spill	Methanol	S	Sulfuric acid, 10%	S
N - Not Recommended	Ethyl alcohol	S	Sulfuric acid, 70%	S
	Skydrol	S	Hydrochloric acid, 10%	S
	Sodium Hydroxide, 10%	S	Vinegar (5% Acetic acid)	S

LiquaTile 1143 has better chemical resistance than most coatings in its class, but in aggressive environments there may be a better choice to resist particular chemicals. Consult Wolverine Coatings Corporation for specific recommendations when chemicals are present.

## EXPLAINING THE TESTS AND THEIR RELEVANCE

**ASTM D523** Gloss is a measurement of the 'perceptible shininess' of a substrate. It is measured using a special tool called a Gloss Meter that calculates the value of specular reflectance measured in GU (Gloss Units). A Gloss Meter shines light on the substrate at a specific angle (typically 20°, 60°, or 85°) and then measures that light on the opposite side at the same angle (specular reflectance). When the emitted light is diffracted the reflected path changes angle and is not returned to the other side which will yield a lower GU number. The more light is reflected to the observer at the same angle the higher the gloss reading in GU (gloss units) and the more 'perceptible shininess' the human will see. The perception of gloss is dependent on the smoothness of the substrate to be coated, the thickness of the applied coating, and the final smoothness of the coated surface. While there is not a specific standard for naming gloss levels the following is a good general guideline: Flat (1–9 GU), Low Sheen (10–25 GU), Eggshell (26–40 GU), Semi Gloss (41–69 GU), Gloss (70–89 GU), High Gloss (>89 GU).

**ASTM D790** Flexural Modulus measures the stiffness (ratio of stress to strain) of a cured coating. Higher modulus yields a stiffer coating that will transmit stresses and strains more directly through the coating surface to the bond line. Low modulus materials will insulate the bond line much like flexible building foundations utilized in earthquake prone areas protect the rigid building from damage caused by movement. See also Flexural Strength.

**ASTM D790** Flexural Strength is measured using a 3 point (or sometimes even a 4 point) bend test. The test defines the amount of stress applied to a material at the point that it moves from a bend to a break (ruptures). The stress (3 point test) is defined as  $\frac{F \cdot L}{b \cdot d^3}$ , where  $F$  is the force applied at the fracture point,  $L$  is the distance (length) between the support spans,  $b$  is the width of the specimen, and  $d$  is the thickness of the specimen. Flexural Strength was not able to be determined on BondTite 1101. An independent laboratory confirmed that this material is highly flexible even at high thicknesses (1/2 inch) and even after being aged. Since the material would never break even at multiple thicknesses and configurations a value could not be determined (even in 15 tests). See also Flexural Modulus.

**ASTM D695** Compressive properties include modulus of elasticity, yield stress, deformation beyond yield point, and compressive strength (unless the material merely flattens but does not fracture). A sample is placed between two plates that are compressed together at a uniform rate. The maximum load at the break point is recorded as well as stress/strain data. When a material does not break the numbers are highly subjective.

**ASTM D638** Elongation is the measure of the ability of a material to stretch. Higher elongation combined with high flexural strength allows a coating to take more punishment from movement without failure. Primers with low elongation are more brittle and can break underneath your coatings system and will eventually result in peeling.

**ASTM D2047** Static Coefficient of Friction is measured in a lab using a machine with a 3" x 3" testing surface known as a James Machine. It is only used for testing dry surfaces, as wet surface testing results come out skewed due to the sensor pads' tendency to hydroplane. In this test, three separate test panels are individually tested with four readings per panel, each panel rotating 90 degrees between each reading to provide a fresh surface and to cancel any directional effects. The panel is placed on the test table in a firm position with the retaining bar. The test material is placed into the strut yoke, at which the entire assembly is then lowered into contact with the test panel. With the hand wheel and recording pen released, the test table is moved forward at a rate of 60 in/min, until the test material slips and the vertical column drops. From the recording pen and chart, the static coefficient of friction is read at the point at which the horizontal curve made on the chart changes to a vertical line. The strut is then lifted and the test table returned to its original position. The test panel is then rotated 90 degrees, the test material sanded, and the steps repeated.

**ASTM D2240** Hardness describes the ability of a material to resist indentation. Hardness is measured using a Durometer which employs a needle that is impressed into the coating. The farther the needle impregnates the coating the lower the measured hardness. Many people mistakenly associate hardness with abrasion (or wear) resistance. While hardness can increase wear resistance of some materials it can also decrease it when a coating is so hard that it becomes brittle (like glass, a very hard but brittle material).

**ASTM D2244** Color is measured using a Spectrophotometer that mathematically defines a color as a point in a three dimensional space. This is defined using a CIELAB set of values. CIELAB uses three plots representing "L" (lightness/darkness), "a" (redness/greenness), and "b" (yellowness/blueness) values. The difference between two measured colors can be described using  $\Delta E$  (pronounced delta E) where  $\Delta E = \sqrt{\Delta L^2 + \Delta a^2 + \Delta b^2}$ .

**ASTM D4060** Taber Abrasion is a test to determine a coating's resistance to wear. Resistance to abrasion is defined as the ability of a material to withstand mechanical action (rubbing, scraping, or erosion). A coated test panel is allowed to cure (dry) and then weighed. The panel is placed on the Taber Abraser. A 1000 gram load is placed on each grinding wheel on the machine and then the wheels are allowed to rest on the coating surface. The machine turns the test panel for 1000 cycles as the grinding wheels abrade the coating. The wheels are resurfaced at the beginning of each test and after 500 cycles. After 1000 cycles the test panel is weighed and the difference between the starting weight and the final weight is recorded. Many companies skew their test results by varying the test parameters. Sometimes you will see only 500 cycles instead of 1000. Many times the weight on the wheels is diminished. Or, a less abrasive wheel is used. For this test to be valid there must be 1000g weights, 1000 cycles, and CS-17 grade wheels must be used.

## LIQUID PHASE PHYSICAL DATA

**ASTM D4541** Bond Strength is a measure of the force required to pull a coating off of a substrate. Many epoxy primers will have higher bond strength to concrete than the tensile strength of the concrete. This means that the concrete will break before the primer can disbond (break). However, the deeper the primer is allowed to penetrate, the more force it will take to break the concrete since the concrete must break further beneath the surface.

**ASTM D5420** Impact Resistance measures the amount of energy a material can absorb without breaking, fracturing, or disbonding. A coating is applied over a steel panel and placed in a Gardner Impact Tester. The falling weight of the tester is dropped at various distances until the coating fractures or breaks. A hit directly to the face of the coating is known as a "Direct" test while a hit to the back of the substrate (steel panel) is considered to be "Indirect". The resistance is expressed in 'Inch Pounds' of force where a higher number is better. The maximum amount of force that can be measured is 320 inch pounds.

## LIQUID PHASE PHYSICAL DATA

PROPERTY	VALUE	TEST METHOD (If applicable)				
Density (Mixed) @ 77°F	15.22 #/Gal	N/A				
Mix Ratio (Volume)	2:1 (A:B)	N/A				
Viscosity (mixed)	2500-4500 cps	ASTM D2196				
Flash Point	Part A >225°C / Part B >97°C	N/A				
<b>Cure Schedule (ASTM D5895)</b>	<b>Temp./Humid.</b>	<b>GelTime</b>	<b>Tack Free</b>	<b>Re-Coat Time</b>	<b>Light Duty</b>	<b>Full Cure</b>
<b>Gel Time (ASTM D2471)</b>	50°F/50% RH	170-190 min.	15-20 hours	24-48 hours	18-22 hours	24-48 hours
<b>LiquaTile 1143 UVR (Standard Cure)</b>	77°F/ 50% RH	90-110 min.	6-8 hours	12-24 hours	9-12 hours	14-24 hours
	95°F / 50% RH	50-80 min.	4-6 hours	10-24 hours	6-9 hours	12-24 hours
<b>Packaging (Shipping Weight lbs.)</b>	3Q - 3/4 gal unit – 1/2 gal Pt. A (4) / Qt. Pt. B (2) 3G - 3 gal unit – 2 gal Pt. A (16) / 1 gal Pt. B (8)					
<b>Shipping</b>	Part A: DOT Regulated Resin Compound, Class 55 Part B: DOT Regulated Resin Compound, Class 55					

## EXPLAINING THE TESTS AND THEIR RELEVANCE

**ASTM D2196** Viscosity is the measurement of the resistance of a liquid to flow. The viscosity profile of the liquid is a factor in the proper installation of the liquid applied coating. The higher the viscosity the thicker the material will be. Viscosity can be affected by temperature, shear stress, or shear rate. The viscosity profile of a material can be classified as Newtonian, Thixotropic, Rheopectic, Pseudoplastic, or Dilatant.

- A Newtonian liquid (like water) would have the same viscosity no matter how much shear force or shear time (from mixing) is exerted on it.
- A Thixotropic material would decrease in viscosity as shear stress is applied to it over time. Once the material is allowed to rest the viscosity increases to its original resting state. Thixotropic fluids require time and shear to thin.
- Rheopectic fluids are the opposite of Thixotropic fluids. The longer shear is maintained on the liquid the higher the viscosity will rise. Rheopectic fluids require time and shear to thicken.
- Pseudoplastics are kind of like thixotropic liquids in that they get thinner when shear is applied. However, Pseudoplastic liquids thin and recover much faster and in more relation to the stress that is applied. Pseudoplastic liquids are more dependant on the force applied instead of the amount of time that the force is applied.
- Dilatant Fluids are the opposite of Pseudoplastic fluids in that they get thicker as more stress is applied. However, like Pseudoplastics the amount of force applied is the driving factor on thickening instead of the amount of time.

**ASTM D5895** The drying (cure) time of a coating can be measured by a Drying Time Recorder where a weighted Teflon stylus is dragged through the coating over time. The 4 stages of dry time (A=Set to Touch, B=Tack-Free Time, C= Dry-Hard Time, and D=Dry-Through Time) are then measured using a template that shows those times in hours.

## INSTALLATION

### SURFACE PREPARATION

Bond strength is directly dependent upon the preparation, strength, and conditions of the substrate. Concrete surfaces should be clean, porous, and textured. Consult WCC TIB: Preparing Concrete to Receive Coatings or Linings. An appropriate primer, typically BondTite 1101, should be used, particularly on uncoated concrete. Steel surfaces should be blasted near white and protected from rusting prior to application. Substrate must be between 40°F and 95°F and at least 5°F above the dew point during installation and cure. Moisture vapor transmission will likely cause coating failure. Always prepare the substrate to receive a coating according to published good painting practices and according to Wolverine Coatings guidelines. Always consult Wolverine Coatings Corporation for other substrates and for specific recommendations for your project.

### MIXING

Consult WCC Technical Information Bulletin (TIB): "Mixing Guide" before installation. Pre-mix all components. Add the ColorMeld (Part C) into the Resin pail. Use a stir stick or paint paddle to empty entire ColorMeld container into the Resin. Mix for 2 minutes, or until ColorMeld is thoroughly incorporated in the Resin (Part A). While mixing at a low speed, slowly add the Hardener (Part B) into the Pigmented Resin pail (Part A+C), taking care to keep material off the side of the pail. Slightly increase speed and mix for 3 minutes, being careful to avoid whipping air into the material. Make sure to occasionally scrape around the mixing pail's walls and edges with a stir stick or spatula to ensure all material has been incorporated and mixed. Apply as soon as possible.

### SAFETY

For your safety, all required personal protection equipment should be used when operating machinery or handling chemicals. Concrete dust is a source of silica particles and other hazardous materials that can cause silicosis and other illnesses. Proper safety equipment and methods are the responsibility of the installation company, general contractor, and/or facility owner.

### WARRANTY

Wolverine Coatings Corporation warrants its products to be free from defects in material and workmanship. Wolverine Coatings Corporation's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at Wolverine Coatings option, to either replacement of products not conforming to this Warranty or credit to the Buyer's account in the invoiced amount of the nonconforming products. Any claim under this warranty must be made by the Buyer to Wolverine Coatings in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the ship date, whichever is earlier. Buyer's failure to notify Wolverine Coatings of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

Wolverine Coatings makes no other warranties about the product. No other warranties, whether expressed, implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply.

Any recommendation or suggestion relating to the use of the products made by Wolverine Coatings, whether in its technical literature, or in response to specific inquiry or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment, changes in procedure of use, or extrapolation of data may cause unsatisfactory results.

### LIMITATION OF LIABILITY

Wolverine Coatings Corporation's liability on any claims based upon Wolverine Coatings Corporation's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or parts thereof which give rise to the claim. In no event shall Wolverine Coatings Corporation be liable for consequential or incidental damages.

### LITERATURE REVISION - TDS: LiquetaTile 1143 - Rev. 231211

Published literature is subject to change without notice. Wolverine Coatings Corporation is constantly engaged in the testing of existing formulations, the development of new innovative technologies, and the evaluation of the latest practices. The latest literature should always be consulted at [www.wolverinecoatings.com](http://www.wolverinecoatings.com).



#### Wolverine Coatings Corporation

5969 Highway 221 | Roebuck, SC 29376

Tel: (864) 587-3144 | Fax: (864) 587-3147

e-mail: [Sales@WolverineCoatings.com](mailto:Sales@WolverineCoatings.com)

website: [www.WolverineCoatings.com](http://www.WolverineCoatings.com)

### APPLICATION

Consult WCC TIB Guide for Applying Resinous Coatings with squeegee and roller. Material may be applied by the squeegee and backroll method. Use high quality, lint free, solvent resistant roller covers. Use throw away chip brushes for cutting in edges. Avoid puddles and missed spots.



### RE-COAT

Consult WCC TIB: Guide for Over-Coating Existing Coatings. Material may be re-coated as soon as it can be walked on without damage. Sanding may be required if coating gets too hard to accept another coat. Consult "Re-coat Time" in "Liquid Phase Physical Data" for guidelines. Be advised that project conditions (including air temperature, substrate temperature, and relative humidity) will influence the "Re-coat Time".

### CLEANING AND MAINTENANCE

Consult WCC TIB: Cleaning and Maintenance